

SOFT-CX is a softening agent for natural or synthetic fibers. Especially it is suitable for cotton, nylon, polyester and T/C fibers. It can be used together with other auxiliaries in resin finishing and shrink resistant finishing.

◆ SPECIFICATION

* APPEARANCE	Milky White Liquid
* IONIC NATURE	Nonionic
* pH (1% aq. Sol'n)	6.0 ± 1.0
* SP.GR(at 25°C)	1.05 ± 0.05
* SOLUBILITY	Easily disperse in cold water.
* STORAGE STABILITY	Min. 1 year under cool and dry conditions when stored in original sealed, packaging.
* COMPATABILITY	Compatible with anionic, nonionic and cationic materials.

◆ FEATURES

- 1) **SOFT-CX** imparts soft touch.
- 2) **SOFT-CX** does not cause a change of color shade or a yellowing after treatment.
- 3) **SOFT-CX** can be used together with all resins and fluorescent bleaching agents.
- 4) There is no yellowing after processing with **SOFT-CX**.
- 5) It is environmental-friendly product as APEO-free and NPEO-free.

◆ APPLICATION FIBERS

Suitable for all kinds of fibers such as Polyester, Nylon, Cotton, T/C, N/C, etc.

◆ HOW TO USE

Recommended use levels are 10-30 g/l according to kinds, density and type of fibers and an objective value.



Ro Chem International SDN BHD

11-3-2, Block-I, Jalan 3/101C, Cheras Business Center
Jalan Cheras, Batu5, 56100, Kuala Lumpur, Malaysia

Cell No : +601116622841, E-mail : info@rochemint.com, www.rochemint.com

◆ RECOMMENDED

RECIPE

1) Processing method of general colored fibers

- **SOFT-SDR** : 10-20 g/ℓ
- **SOFT-CXR** : 10-20 g/ℓ
- **ANTIC-RDK** : 10-20 g/ℓ
- **ANTIC-RDK** : Padding at room temperature.
- Processing method : Dry 50-80 m/min at 170-180°C after passing 3 Kg/ cm² mangle.
- Dry conditions : 50-70%
- Pick Up

2) Processing method of white and light colored fibers

- **SOFT-RDC** : 10-20 g/ℓ
- **SOFT-NXR** : 10-20 g/ℓ
- **SOFT-NXR** : 10-20 g/ℓ
- **ANTICX-KNR** : 10-20 g/ℓ
- **ANTICX-KNR** : Padding at room temperature.
- Processing method : Dry 50-80 m/min at 170-180°C after passing 3 Kg/ cm² mangle.
- Dry conditions : 50-70%
- Pick Up

◆ PACKAGE

120 Kgs NET IN DRUMS.



Ro Chem International SDN BHD

11-3-2, Block-I, Jalan 3/101C, Cheras Business Center
Jalan Cheras, Batu5, 56100, Kuala Lumpur, Malaysia

Cell No : +601116622841, E-mail : info@rochemint.com, www.rochemint.com