



ROCOFLUID CN Textile Finishing Agent

Foam free Crease Preventing Agent & Lubricant

Characteristic: Acrylic acid derivative.

Appearance : Colourless Pale viscous liquid.

Ionic State : Non-ionic.

- **ROCOFLUID CN (Textile Finishing Agent)** is a foamless crease preventing agent and lubricant for the dyeing of cotton, viscose, wool synthetics, as well as their blends. **ROCOFLUID CN (Textile Finishing Agent)** is particularly designed for the bleaching, dyeing and washing of fabrics in rope form.
- **ROCOFLUID CN (Textile Finishing Agent)** imparts to the treated fabrics very good sliding properties and smoothness thus creating the best conditions to obtain crease-free dyed goods. The inclusion of **ROCOFLUID CN (Textile Finishing Agent)** into the processing bath promotes adhesion of the bath to the fabric and hence increases the level of hydrodynamic lubricity between fabric to fabric and fabric to vessel surfaces. Chafe marks can be minimized by the function of **ROCOFLUID CN (Textile Finishing Agent)** As a non-ionic product, **ROCOFLUID CN (Textile Finishing Agent)** is compatible with all non-ionic, anionic and cationic dyestuffs and agents. **ROCOFLUID CN (Textile Finishing Agent)** is resistant to high temperatures. The product has no levelling or dispersing affect.

pH : 6 - 7

Solubility : Soluble in water at any ratio.

Stability : Stable in high acidic and alkali conditions.





Application : It's suitable for dyeing of fabrics which is cellulosic, wool and synthetics and their blends with all kinds of dyestuffs.

Bleaching;

- **ROCOFLUID CN (Textile Finishing Agent)** is diluted with cold water and given to the bath with the addition of a wetting agent. At the next stage, fabric is taken and the rest of the chemicals are introduced to the bath. Recommended amount of **ROCOFLUID CN (Textile Finishing Agent)** varies between 1 - 2 % due to fabric properties (eg. thickness).

Dyeing;

- **ROCOFLUID CN (Textile Finishing Agent)** is taken to the bath after dilution with cold water, then the rest of the dyeing process is completed. The recommended amount is 1 - 2 %.

Finishing;

- **ROCOFLUID CN (Textile Finishing Agent)** due to its non-ionic nature, it can be easily used with softening agent in the finishing bath. This is specially recommended for centrifuge drying. 0,5 - 1 % is advised quantity for this purpose.

Storage : 2 years.

